

PAINTCOR

SUPREME QUALITY *From 2086*

AQUASEAL SATURATOR

Technical Specifications

Vehicle Type	Modified Acrylic
Solvent	Water
Enviro Rating	Conforms to EU 2010 V.O.C. Rules
Dilution/Thinning	Ready for use
Theoretical Spread Rate	1m ² per litre if used with membrane 8 m ² per litre on sealed surfaces
Apply With	Brush, roller or spray
Drying Time	1 hour @ 25°C
Washability	Good
Elongation	450%
Pigment	Red oxide
Viscosity at 25°C	Supplied ready for use
Solids Volume	± 35%
Flexibility	Excellent
Colour	Red, pinkish colour.
Finish	Sheen
Storage	Cool, dry place
Overcoating	Paintcor's AquaSeal or Elegance (Glo)
Packaging	1l, 5l and 20l
Guarantee	5 Years if overcoated with Aquaseal
Conditions of Guarantee	Annual inspections must be carried out on the waterproofing systems for any defects or blocked drainage (service contract)
Resistance to Water	Excellent
Resistance to Solvents	Some solvents
Specific Gravity	1.17 - 1.18
Impact Resistance	Good
Active Ingredient	N/A
Additional Amount	N/A
Caution	Safe, Non-Toxic, Non-Flammable
Catalyst Ratio	N/A
Recommended Dry Film	40-50µm micron per coat
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	1000 hours - No degradation
Appearance	Emulsion paint

Note: AquaSeal Saturator has been designed for water resistance. Best weathering ability is achieved using Paintcor AquaSeal or Elegance (Glo) as a top coat.