

PAINTCOR

SUPREME QUALITY *Since 1986*

ALL PRIME

Technical Specifications

| | |
|-------------------------|--|
| Vehicle Type | Modified Acrylic |
| Solvent | Water |
| Enviro Rating | VOC 5% less |
| Dilution / Thinning | No more than 10% water for spraying |
| Theoretical Spread Rate | Primed steel 10m ² per litre |
| Apply with | Brush, roller or spay |
| Drying time | @ 25°C ± 30 minutes per coat |
| Wash ability | N/A |
| Elongation | Good |
| Pigment | Anti-corrosive pigments |
| Solids Volume | ± 46 |
| Flexibility | Good |
| Colour | Red Oxide |
| Finish | Matt |
| Storage | Cool, dry place |
| Over coating | Undercoat and / or top coat of your choice |
| Packaging | 1L, 5L, 20L |
| Guarantee | N/A |
| Conditions of Guarantee | N/A |
| Resistance to Water | Good |
| Resistance to Solvents | N/A |
| Impact Resistance | N/A |
| Active Ingredient | Zinc Phosphate, Anti-Corrosive Pigment |
| Additional Amount | N/A |
| Caution | Safe, Non-Toxic, Non-Flammable |
| Catalyst Ratio | N/A |
| Recommended Dry Film | 40 micron per coat |
| Freeze Thaw | Pass |
| Accelerated Stability | Pass |
| Accelerated Weathering | N/A |
| Appearance | Red Emulsion Paint |

NOTE: Allow AllPrime to dry for 12 hours if overcoating with a solvent based top coat.

Paintcor cc

Reg No: CK 86/19456/23

VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za
Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited

