

PAINTCOR

SUPREME QUALITY *Since 1986*

AQUASEAL SATURATOR AND TOP COAT

Technical Specifications

Vehicle Type	Modified Acrylic
Solvent	Water
Enviro Rating	VOC 5% less
Dilution / Thinning	Supplied ready for use
Theoretical Spread Rate	1m ² per litre if used with membrane 8 m ² per litre on sealed surfaces
Apply with	Brush, Roller or spray
Drying time	@ 25°C , 30 minutes per coat (without bandage)
Wash ability	Good
Elongation	450%
Pigment	Inert pigment, fillers and extenders
Solids Volume	± 34%
Flexibility	Excellent
Colour	5 Standard colours (see Paintcor's colour chart)
Finish	Sheen
Storage	Cool, dry place
Over coating	Paintcor's Elegance (Silk), RuvAcryl or AquaSeal Top Coat
Packaging	1L, 5L, 20L
Guarantee	5 Years (AquaSeal top coat)
Conditions of Guarantee	Annual inspections must be carried out on waterproofing system and cracking must be rectified (service contract)
Resistance to Water	Excellent
Resistance to Solvents	Some solvents
Impact Resistance	Good
Active Ingredient	N/A
Additional Amount	N/A
Caution	Safe, Non-Toxic, Non-Flammable
Catalyst Ratio	N/A
Recommended Dry Film	30 - 40µm per coat
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	1 000 hours – no degradation
Appearance	Emulsion paint

Note: AquaSeal has been designed for water resistance. Best weathering ability is achieved using Paintcor Elegance for final coats.

Paintcor cc
Reg No: CK 86/19456/23
VAT No: 4830119311
Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za
Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited

