

PAINTCOR

SUPREME QUALITY *Since 1986*

ECONOCRYL

Technical Specifications

Vehicle Type	Modified Acrylic Co-polymer
Solvent	Water
Enviro Rating	Conforms to EU 2010 V.O.C. rules
Dilution / Thinning	Supplied ready for use
Theoretical Spread Rate	±6m ² per litre
Apply with	Brush, Roller or Spray
Drying time	@ 25°C ± 20 minutes between coats
Wash ability	Poor
Elongation	None
Pigment	Pigmented
Solids Volume	30 - 31%
Flexibility	None
Colour	White and pastel colours
Finish	Matt
Storage	Cool, dry place.
Over coating	Top Coat of your choice
Packaging	1L, 5L and 20L
Guarantee	N/A
Conditions of Guarantee	N/A
Resistance to Water	Poor
Resistance to Solvents	Poor
Impact Resistance	N/A
Active Ingredient	N/A
Additional Amount	N/A
Caution	Safe, Non-Toxic, Non-Flammable
Catalyst Ratio	N/A
Recommended Dry Film	30µm per coat
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	Pass
Appearance	White Emulsion Paint

Paintcor cc
Reg No: CK 86/19456/23
VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za
Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited

