

PAINTCOR

SUPREME QUALITY *Since 1986*

EPOXIPRIME

Technical Specifications

Vehicle Type	Epoxy
Solvent	M.I.B.K
Enviro Rating	Flammable 3
Dilution / Thinning	Supplied ready for use. See application for spray thinning.
Theoretical Spread Rate	±15m ² per litre. Cementitious surface: 8m ² per litre: This rate will differ Dependant on how absorbent the surface is, can be as low as 4m ² per litre per coat
Apply with	Brush, Roller or spray
Drying time	@ 25°C ± 12 hours to Tacky. @ 25°C ± 18 hours to Hard dry.
Wash ability	N/A
Elongation	N/A
Pigment	Non-Pigmented
Solids Volume	89%
Flexibility	Good
Colour	Clear
Finish	N/A
Storage	Cool, dry place. Keep out of reach of children.
Over coating	Between Primer coats: ±18 hours @25°C / Between Primer & Top coat: ±12 hours @25°C
Packaging	2Kg with 1Kg Catalyst / 400g with 200g Catalyst
Guarantee	N/A
Conditions of Guarantee	N/A
Resistance to Water	Excellent
Resistance to Solvents	Excellent
Impact Resistance	Excellent
Active Ingredient	N/A
Additional Amount	N/A
Caution	Flammable
Catalyst Ratio	100grams Primer: 35.65 grams Catalyst
Recommended Dry Film	15 - 20um per coat (Osmotic barrier 2 – 4 coats)
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	N/A
Appearance	Amber coloured resin once mixed with Catalyst

Note: Application directions must be strictly followed for this product to perform to its full potential. This product carries no guarantee once applied.

Paintcor cc
Reg No: CK 86/19456/23
VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za
Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited

