

PAINTCOR

SUPREME QUALITY *Since 1986*

FLASHSKIM INTERIOR

Technical Specifications

Vehicle Type	Modified Acrylic
Solvent	Water
Enviro Rating	VOC 5% or less
Dilution / Thinning	Supplied ready for use
Theoretical Spread Rate	2 - 4m ² per litre
Apply with	Trowel, Scraper
Drying time	@ 25°C -30 minutes @ 0.5mm thick.
Wash ability	N/A
Elongation	N/A
Pigment	White
Solids Volume	56.5%
Flexibility	N/A
Colour	White
Finish	Smooth
Storage	Cool, dry place.
Over coating	Undercoat or top coat of your choice
Packaging	250ml, 500ml, 1L, 5L and 20L
Guarantee	N/A
Conditions of Guarantee	N/A
Resistance to Water	Fair
Resistance to Solvents	Poor
Impact Resistance	N/A
Active Ingredient	N/A
Additional Amount	N/A
Caution	Safe, Non-toxic, Non-flammable
Catalyst Ratio	N/A
Recommended Dry Film	4mm maximum
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	N/A
Appearance	Thick, White paste

Note: *FlashSkim is for Interior use only.*

Paintcor cc

Reg No: CK 86/19456/23

VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za
Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited

