

PAINTCOR

SUPREME QUALITY *Since 1986*

FLOORCOAT

Description and Application

CATEGORY

Floor Coating

DESCRIPTION

FloorCoat Alkyd Polyurethane Floor Paint has been formulated for domestic and light industrial concrete floors. It dries to a tough durable finish with excellent adhesion. Paintcor's FloorCoat is not recommended for exterior use. It is supplied in a range of standard colours and has a medium gloss finish.

FEATURES

- FloorCoat is a tough, durable, thin film floor paint system - designed to be resistant to most household chemicals.
- Single pack (requires no catalyst)

SURFACE PREPARATION AND APPLICATION METHOD

NEW OR UNPAINTED FLOORS

1. Clean floor and degrease if necessary.
2. Acid wash floor with undiluted hydrochloric acid (pool acid) and rinse well (immediately) with fresh water. There must be no acid left on the floor. Allow to dry.
3. Apply the first coat of FloorCoat DILUTED 10% with mineral turpentine. Allow 6 hours to dry @ 25°C.
4. Apply second coat of UNDILUTED FloorCoat. Allow to dry.

PREVIOUSLY PAINTED FLOORS

NOTE: This product is not compatible with all floor coatings e.g. (FloorCoat cannot be used over epoxy floor coating). If you are in any doubt as to Paintcor's FloorCoat's compatibility please contact our Technical Support Team on (011) 794-4599.

1. Remove any loose peeling paint. If unpainted concrete areas are exposed, treat as for new concrete.
2. Degrease floor if necessary. Rinse well and allow to dry.
3. Sand existing floor paint to a clean matt finish. Remove sanding dust. Ensure floor is dry.

Paintcor cc

Reg No: CK 86/19456/23

VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za

Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited



PAINTCOR

SUPREME QUALITY *Since 1986*

4. Prime expose concrete with 1 coat of Paintcor's FloorCoat DILUTED with 10% mineral turpentine. Allow 6 hours to dry @ 25°C.
5. Apply 2 coats UNDILUTED FloorCoat. Allow to dry between coats.

APPLICATION METHOD

Brush, roller or airless spray.

CLEANING EQUIPMENT

Clean equipment with Mineral Turpentine or Lacquer Thinners immediately after use.

Paintcor cc

Reg No: CK 86/19456/23

VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za

Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited

