

PAINTCOR

SUPREME QUALITY *Since 1986*

HIGLO

Technical Specifications

| | |
|-------------------------|--|
| Vehicle Type | Long Oil Alkyd |
| Solvent | Turpentine |
| Enviro Rating | Flammable |
| Dilution / Thinning | Supplied ready for use |
| Theoretical Spread Rate | 10m ² per litre |
| Apply with | Brush, Roller or Spray |
| Drying time | Surface Dry: 2 hours Hard Dry: 7 hours |
| Wash ability | Excellent |
| Elongation | N/A |
| Pigment | Pigmented |
| Solids Volume | ± 40 |
| Flexibility | Fair |
| Colour | Colour of your choice |
| Finish | High Gloss |
| Storage | Cool, dry place. |
| Over coating | N/A |
| Packaging | 1L, 5L and 20L |
| Guarantee | N/A |
| Conditions of Guarantee | N/A |
| Resistance to Water | Excellent |
| Resistance to Solvents | Good |
| Impact Resistance | Pass |
| Active Ingredient | N/A |
| Additional Amount | N/A |
| Caution | Flammable (see Material Safety Data sheet) |
| Catalyst Ratio | N/A |
| Recommended Dry Film | 30 - 40µm |
| Freeze Thaw | Pass |
| Accelerated Stability | Pass |
| Accelerated Weathering | Pass |
| Appearance | High gloss enamel paint |

Note: *White will yellow in areas that are in continual darkness*

Paintcor cc
Reg No: CK 86/19456/23
VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za
Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited

