

PAINTCOR

SUPREME QUALITY *Since 1986*

KLINKASEAL

Technical Specifications

Vehicle Type	Silane / Siloxane
Solvent	Turpentine
Enviro Rating	Flammable
Dilution / Thinning	Not more than 20% of product with Turps
Theoretical Spread Rate	±15m ² per litre
Apply with	Brush, Rag, Sponge, Roller or Spray
Drying time	N/A
Wash ability	N/A
Elongation	N/A
Pigment	Non-Pigmented
Solids Volume	N/A
Flexibility	N/A
Colour	Transparent
Finish	N/A
Storage	Cool, dry place.
Over coating	Can be over coated with emulsion paint. (See Application Date)
Packaging	1L, 5L and 20L
Guarantee	N/A
Conditions of Guarantee	N/A
Resistance to Water	Excellent
Resistance to Solvents	N/A
Impact Resistance	N/A
Active Ingredient	N/A
Additional Amount	N/A
Caution	Flammable (see Material Safety Data sheet)
Catalyst Ratio	N/A
Recommended Dry Film	N/A
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	N/A
Appearance	Transparent liquid

Note: *The plaster to which KlinkaSeal is applied must be of high quality if it is going to be painted with emulsion Paints. Please call us for technical assistance if the plaster is poor and friable. Do NOT apply to such a surface.*

Paintcor cc
Reg No: CK 86/19456/23
VAT No: 4830119311
Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za
Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited

