

PAINTCOR

SUPREME QUALITY *Since 1986*

PALLETGUARD

Technical Specifications

Vehicle Type	Pure Acrylic (Adhesion Promoted)
Solvent	Water
Enviro Rating	Conforms to EU 2010 V.O.C. rules
Dilution / Thinning	Supplied ready for use
Theoretical Spread Rate	8 - 10m ² per litre per coat (Hard wood) 6 - 8m ² per litre per coat (Soft wood)
Apply with	Brush, Roller or spray
Drying time	@ 25°C @ ±25 minutes per coat
Wash ability	Excellent
Elongation	200%
Pigment	Pigmented
Solids Volume	33
Flexibility	Excellent
Colour	Colours of your choice
Finish	Sheen
Storage	Cool, dry place
Over coating	@ 25°C @ ± 1 hour
Packaging	1L, 5L, 20L
Guarantee	N/A
Conditions of Guarantee	N/A
Resistance to Water	Excellent
Resistance to Solvents	Good
Impact Resistance	Good
Active Ingredient	N/A
Additional Amount	N/A
Caution	Safe, Non-Toxic, Non-Flammable (See Material Safety Data Sheets)
Catalyst Ratio	N/A
Recommended Dry Film	33 um per coat
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	Excellent
Appearance	Emulsion paint

Note: For best wood protection results, all areas of the wood must be sealed with PalletGuard. This will require atleast 2 – 3 coats.

Paintcor cc
Reg No: CK 86/19456/23
VAT No: 4830119311
Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za
Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited

