

PAINTCOR

SUPREME QUALITY *Since 1986*

PLASTERBOND

Technical Specifications

Vehicle Type	Modified Acrylic
Solvent	Water
Enviro Rating	Conforms to EU 2010 V.O.C. Rules
Dilution / Thinning	Supplied ready for use
Theoretical Spread Rate	12m ² per litre
Apply with	Brush, roller or spay
Drying time	20 minutes @ 25°C
Wash ability	N/A
Elongation	Good
Pigment	Non-Pigmented
Solids Volume	12%
Flexibility	N/A
Colour	Milk White
Finish	N/A
Storage	Cool, dry place
Over coating	N/A
Packaging	1L, 5L, 20L
Guarantee	N/A
Conditions of Guarantee	N/A
Resistance to Water	Good
Resistance to Solvents	N/A
Impact Resistance	Good
Active Ingredient	N/A
Additional Amount	N/A
Caution	Safe, Non-Toxic, Non-Flammable (See Material Safety Data Sheet)
Catalyst Ratio	N/A
Recommended Dry Film	N/A
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	N/A
Appearance	Milky liquid

Paintcor cc

Reg No: CK 86/19456/23

VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za

Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited

