

# PAINTCOR

SUPREME QUALITY *Since 1986*

## PLASTERPRIME

### Technical Specifications

Vehicle Type	Acrylic
Solvent	Water-borne
Enviro Rating	Water-based Low V.O.C.
Dilution / Thinning	Do not dilute
Theoretical Spread Rate	12 - 15m <sup>2</sup> per litre
Apply with	Brush, roller or spay
Drying time	Touch dry: @ 25°C – 1 hour / Over coating: @ 25°C – 2 hours
Washability	N/A
Elongation	Fair
Pigment	Pigmented (Off-white)
Solids Volume	± 38%
Flexibility	Fair
Colour	Off White
Finish	Matt
Storage	Cool, dry place. Keep out of reach of children.
Over coating	Any of Paintcor's water based top coats.
Packaging	1L, 5L, 20L
Guarantee	N/A
Conditions of Guarantee	N/A
Resistance to Water	Excellent
Resistance to Solvents	Fair
Impact Resistance	Good
Active Ingredient	N/A
Additional Amount	N/A
Caution	Water-borne
Catalyst Ratio	N/A
Recommended Dry Film	38 micron (maximum) per coat
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	N/A
Appearance	Off-white paint

**Note: For best performance, follow application instructions.**

#### Paintcor cc

Reg No: CK 86/19456/23

VAT No: 4830119311

Members: G. Williams, G. Adendorff  
W. Williams

Head office: 1494 Mailship  
street, Laser Park, Honeydew, 2040  
Postal Address: P.O. Box 917,  
Northriding, 2162  
RSA

Email  
sale@paintcor.co.za

Website  
www.paintcor.co.za

Tel: 011 794 2885  
Fax no: 011 794 6955  
Emergency Numbers  
+27(0) 79 526 1565  
+27(0) 84 305 5636



VERY LOW  
VOC

**SABS**  
ISO 9001 Accredited

