

PAINTCOR

SUPREME QUALITY *Since 1986*

PRISTINA

Technical Specifications

Vehicle Type	Pure Acrylic
Solvent	Water
Enviro Rating	Conforms to EU 2010 V.O.C. rules
Dilution / Thinning	Supplied ready for use
Theoretical Spread Rate	New Plaster: $\pm 4\text{m}^2$ per litre Previously Painted Plaster: $\pm 8\text{m}^2$ per litre
Apply with	Brush, Roller or spray
Drying time	@ 25°C @ 30 minutes per coat
Wash ability	Washable
Elongation	N/A
Pigment	Pigmented
Solids Volume	$\pm 34\%$
Flexibility	Low
Colour	Colours of your choice
Finish	Matt
Storage	Cool, dry place
Over coating	@ 25°C @ ± 1 hour per coat
Packaging	1L, 5L, 20L
Guarantee	5 Years
Conditions of Guarantee	Products to be applied to manufacturer's specifications. Areas below damp proof course, boundary walls and structural defects are not covered by this guarantee.
Resistance to Water	Allows vapour transmission
Resistance to Solvents	Poor
Impact Resistance	N/A
Active Ingredient	N/A
Additional Amount	N/A
Caution	Safe, Non-Toxic, Non-Flammable (See Material Safety Data Sheet)
Catalyst Ratio	N/A
Recommended Dry Film	30 microns (minimum) per coat
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	Pass
Appearance	Emulsion paint

Paintcor cc

Reg No: CK 86/19456/23

VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za
Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited

