

# PAINTCOR

SUPREME QUALITY *From 2086*

## RUSCON

### Technical Specifications

Vehicle Type	Acrylic
Solvent	Water
Enviro Rating	Conforms to EU 2010 V.O.C. Rules
Dilution/Thinning	Supplied ready for use
Theoretical Spread Rate	17-20m <sup>2</sup> per litre
Apply With	Brush, roller or airless spray
Drying Time	@ 25°C - 1 hour (Touch dry) Over Coat (Water Based ±4 hours) or (Solvent ±12 hours).
Washability	N/A
Elongation	200%
Pigment	Rust Conversion
Viscosity at 25°C	62 - 70 Kμ
Solids Volume	N/A
Flexibility	Excellent
Colour	Pinkish Brown
Finish	Black Sheen
Storage	Cool, dry place
Overcoating	Anti corrosive - (Primer/Top Coat), AllPrime or most anti corrosive primers
Packaging	1l, 5l
Guarantee	N/A
Conditions of Guarantee	N/A
Resistance to Water	Very Good
Resistance to Solvents	N/A
Specific Gravity	1.06 - 1.08
Impact Resistance	N/A
Active Ingredient	Polyphenols
Additional Amount	N/A
Caution	Non-Flammable
Catalyst Ratio	N/A
Recommended Dry Film	15-20μm
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	N/A
Appearance	Pinkish Brown Emulsion Paint