

# PAINTCOR

SUPREME QUALITY *From 2086*

## RUVACRYL

### **SABS** SABS Test Report

ISO 9001

All Information on this page was copied from SABS Final Test Report Number: 5536/1597769/T463A Dated: 19-11-2001

This report relates only to the specific sample(s) tested as identified herein. It does not imply SABS approval of the quality and / or performance of the item(s) in question and the test results do not apply to any similar item that has not been tested. (Refer also to the complete conditions printed on the back of the official test reports.)

#### Testing of one Roof Paint Final Report

##### 1. Description of Sample:

The following sample was submitted by Mr G. Williams of Paintcor CC on 11 June 2001 and received in good order and suitable for testing.

SABS Code	Quantity	Sample Description
T463	1 x 500ml	Roof Paint marked: Nutmeg, Colour - Brown

##### 2. Test Requested

Test the sample of roof paint against the relevant requirements of SABS 940:1999 for a tiled pitched roof.

##### 3. Test Methods

The sample was tested in accordance with the requirements of SABS 1227:1986 .

##### 4. Test Duration

Testing commenced on 11 December 2000 and was completed on 16 November 2001.

##### 5. Results (Note: C = complies)

Property	Evaluation	Requirements of SABS 1586:1995
Condition in container	C	Subclause 4.1
Reducibility with water	C	Subclause 4.2.1
Brush application	C	Subclause 4.2.2
Roller application	C	Subclause 4.2.3
Spray application	C	Subclause 4.2.4



**PAINTCOR**  
MANUFACTURERS

High temperature stability	Insufficient sample	Subclause 4.3.1
Freeze-thaw stability	Insufficient sample	Subclause 4.3.2
Shelf life, 30 days	C	Subclause 4.3.3
Gloss 85°	2,4	<10
Low temperature film formation	C	Subclause 4.9
Flexibility	C	Subclause 4.10
Hiding power, %	0,986	0,98 minimum
Artificial weathering	No visible defects	Subclause 4.9
Natural weathering	C	Subclause 4.8

**6. Conclusion**

This sample complies with the requirements of SABS 940:1999.