

# PAINTCOR

SUPREME QUALITY *Since 1986*

## RUVACRYL

### Technical Specifications

Vehicle Type	Pure Acrylic (Modified)
Solvent	Water
Enviro Rating	Conforms to EU 2010 V.O.C. rules
Dilution / Thinning	May be thinned no more than 10% with water for spray application only
Theoretical Spread Rate	8 - 9m <sup>2</sup> per litre
Apply with	Brush, Roller or airless spray
Drying time	@ 25°C – 30 minutes per coat
Wash ability	Excellent
Elongation	Good
Pigment	Pigmented
Viscosity @25°C	Ready to use
Flexibility	Very Good
Colour	Paintcor's standard roof colours
Finish	Suede
Storage	Cool, dry place
Over coating	@ 25°C - ± 2 hours between coats
Packaging	1L, 5L and 20L
Guarantee	10 Years
Conditions of Guarantee	Product to be applied to manufacturers specifications. Areas below damp proof course, boundary walls and structural defects are not covered by this guarantee.
Resistance to Water	Good
Resistance to Solvents	Fair
Impact Resistance	N/A
Active Ingredient	N/A
Additional Amount	N/A
Caution	Safe, Non-Toxic, Non-Flammable
Catalyst Ratio	N/A
Recommended Dry Film	35µm per coat
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	Pass
Appearance	Emulsion Paint

**Note:** Ruvacryl can take ponding water and can be used as a maintenance coat over acrylic water proofing systems.

**Paintcor cc**  
Reg No: CK 86/19456/23  
VAT No: 4830119311

**Members:** G. Williams, G. Adendorff  
W. Williams

**Head office:** 1494 Mailship  
street, Laser Park, Honeydew, 2040  
**Postal Address:** P.O. Box 917,  
Northriding, 2162  
RSA

**Email**  
sale@paintcor.co.za  
**Website**  
www.paintcor.co.za

**Tel:** 011 794 2885  
**Fax no:** 011 794 6955  
**Emergency Numbers**  
+27(0) 79 526 1565  
+27(0) 84 305 5636



**SABS**  
ISO 9001 Accredited

