

PAINTCOR

SUPREME QUALITY *Since 1986*

SUBTEX

Technical Specifications

Vehicle Type	Styrene Acrylic
Solvent	Water
Enviro Rating	Conforms to EU 2010 V.O.C. Rules
Dilution / Thinning	Supplied ready for use
Theoretical Spread Rate	Ripple Roller (Textured): $\pm 3\text{m}^2$ / litre Sheepskin Roller: $\pm 4.5 - 5\text{m}^2$
Apply with	Brush or roller
Drying time	@ 25°C - 1 hour
Wash ability	N/A
Elongation	Low
Pigment	Pigmented
Viscosity @ 25°C	Ready for use
Solids Volume	$\pm 52\%$
Flexibility	N/A
Colour	White
Finish	Matt
Storage	Cool, dry place.
Over coating	3 hours @ 25°C
Packaging	1L, 5L and 20L
Guarantee	N/A
Conditions of Guarantee	N/A
Resistance to Water	Good
Resistance to Solvents	N/A
Impact Resistance	N/A
Active Ingredient	N/A
Additional Amount	N/A
Caution	Safe, Non-Toxic, Non-Flammable
Catalyst Ratio	N/A
Recommended Dry Film	50 – 100um per coat
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	N/A
Appearance	Thick white emulsion coating

Note: If SubTex is applied with a textured roller, new plaster must first be sealed with Paintcor's AcrySeal to prevent the plaster absorbing the binder out of SubTex, causing it to crack. Please contact our Technical Department for training on application with a textured roller

Paintcor cc

Reg No: CK 86/19456/23

VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za
Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited

