

PAINTCOR

SUPREME QUALITY *Since 1986*

TERRAFIRMA

Description and Application

CATEGORY

Floor coating

DESCRIPTION

Terrafirma driveway and paving paint is a hard, durable coating formulated to be fast drying, non-slip and very resistant to the sun. It can be used on porous brick and paving and is obtainable in a range of tinted colours. Terrafirma will adhere to most surfaces, including some plastics.

FEATURES

- It is quick Drying.
- It is adhesion Promoted.
- It is slip resistant.
- It has very good UV resistance.
- It is durable.
- Good hot-tyre resistance.

Other uses

Paintcor's Terrafirma can be used on flower pots and other kinds of plastic garden furniture. It can also be used on walls and roofs.

SURFACE PREPARATION AND APPLICATION

SURFACE PREPARATION

Unpainted brick or paving

1. Degrease surface area if necessary. Wash down surface area to remove all dirt and tyre grit.
2. Rinse well and allow sufficient time to dry.
3. Apply one coat of Terrafirma, diluted with 20% water to all paving.
4. Allow a drying time of approximately 1 hour at 25 degrees C.
5. Apply a second, undiluted coat of TerraFirma. Allow sufficient time to dry.

NOTE: Do not leave the product in the bucket uncovered, as a layer of skin will form on top of the paint.

Paintcor cc

Reg No: CK 86/19456/23
VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za
Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited



PAINTCOR

SUPREME QUALITY *Since 1986*

Previously painted surfaces

1. Wash the surface area down to remove dirt, dust and oil.
2. Allow sufficient time to dry.
3. Remove loose, peeling paint if necessary.
4. Ensure that any old paint is adhering well to the brick surface.
5. Cure the surface area of algae if necessary, using Paintcor's Ushevu algae killer. (See Data Sheet for use).
6. Apply one coat of Terrafirma, diluted with 20% water, to any area where paint has been removed. Allow a drying time of approximately 1 hour at 25 degrees.
7. Finally apply two undiluted top coats. Allow sufficient time to dry in between coats.

APPLICATION METHOD

1. Apply using a brush, roller or airless spray.

NOTE: This product is not recommended for use over old enamel or polyurethane paint systems. Adhesion to the existing system must first be checked. Call Paintcor's Technical Department on 011 794-2885 for assistance.

CLEANING EQUIPMENT

Clean all equipment with water immediately after use.

Paintcor cc
Reg No: CK 86/19456/23
VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za
Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited

