

PAINTCOR

SUPREME QUALITY *Since 1986*

TERRAFIRMA

Technical Specifications

Vehicle Type	Modified Pure Acrylic Adhesion Promoted
Solvent	Water
Enviro Rating	VOC 5% or less
Dilution / Thinning	Supplied ready for use
Theoretical Spread Rate	± 8m ² per litre
Apply with	Brush, Roller or Spray
Drying time	Touch Dry: 15minutes @ 25°C Overcoatable: 1 hour @ 25°C Cars can be parked on the drive within 12 hours
Wash ability	Good
Elongation	100%
Pigment	Pigmented
Solids Volume	40%
Flexibility	N/A
Colour	Available in dark colours and Paintcor standards colours only
Finish	Suede
Storage	Cool, dry place.
Over coating	N/A
Packaging	1L, 5L and 20L
Guarantee	N/A
Conditions of Guarantee	N/A
Resistance to Water	Excellent
Resistance to Solvents	Fair
Impact Resistance	Good
Active Ingredient	N/A
Additional Amount	N/A
Caution	Non-Flammable but contains Methanol
Catalyst Ratio	N/A
Recommended Dry Film	40 µm per coat
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	Pass
Appearance	Emulsion Paint

Note: *This product is NOT to be used on power-floated floors, (hot tyres could pull product from the surface), or interior floors where gloss and a high degree of clean-ability and chemical resistance is necessary.*

Paintcor cc

Reg No: CK 86/19456/23

VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za
Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited

