

PAINTCOR

SUPREME QUALITY *Since 1986*

WOOD1ST

Description and Application

CATEGORY

Wood treatment

DESCRIPTION

Wood1st has been developed to protect and stain (if necessary) both new and raw wood. It can be used alone, or as a deep penetrating primer under varnish. Wood1st contains deep penetrating oils, alkyds, pesticides and UV stabilizers. It feeds, nourishes and protects all wood from various weather conditions and mould.

FEATURES

- It can be used as a deep penetrating wood dressing or as a sealer before varnish.
- It Nourishes natural wood types.
- It protects against elements and acts as a UV stabilizer.
- It creates a deep penetrating pre-varnish treatment (alkyds).

SURFACE PREPARATION AND APPLICATION

Used alone

1. Ensure that the wood is raw, new and/or untreated.
2. Sand the wood down to a clean smooth finish, remove any sanding dust.
3. Use Wood1st undiluted.
4. Apply one or two coats of Wood1st as is, or use more to stain to your liking.
5. Hard woods require one coat whereas soft woods require two coats.
6. When wood starts to look dry (1 to 2 years after initial application), sand lightly and apply additional coats.

Used as an undercoat prior to applying a varnish on outdoor surfaces

In order to achieve the best performance from an exterior varnish system it is essential to nourish, preserve and protect the wood before applying the varnish. This will significantly prolong the life span of the varnish and the natural wood. It is therefore important to apply Wood1st before varnishing exterior wood. For your convenience, Wood1st is available in various stains. Applying Woodluc or Woodcoat clear varnish over Wood1st will result in a rich finish that will enhance the natural grain of the wood.

1. Dilute Wood1st with 20% Turpentine (For hard wood only).

Paintcor cc

Reg No: CK 86/19456/23
VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za
Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



VERY LOW
VOC

SABS
ISO 9001 Accredited



PAINTCOR

SUPREME QUALITY *Since 1986*

2. Ensure that the natural wood is raw, new and untreated.
3. Sand the wood to a clean smooth finish, remove any sanding dust.
4. Apply a liberal coat of Paintcor's Wood1st to all sides of the wood. (For best results apply Wood1st to all areas of the wood prior to assembly).
5. Allow a drying time of 6 hours at 25°C in between coats and 12 hours before over-varnishing.
6. One coat of Wood1st is sufficient for hard woods. Softer woods require at least two coats of Wood1st.
7. Apply two coats of Paintcor's WoodLuv or WoodCoat varnish to areas of wood prior to installation.
8. Allow sufficient time to dry in between coats.
9. Once installation has taken place, apply 2 - 3 coats of Paintcor's WoodLuv or WoodCoat to all exposed areas. This will seal all screw and/or nail fitment points.
10. Allow up to 6 hours to dry in between coats.

NOTE: In order to prolong the life-span of the installation outdoors, it is important to feed and seal all areas of the wood, including fixing points.

11. Drying times are at 25°C. Additional drying time should be made by adding ½ an hour for every degree below 25°C.

CLEANING EQUIPMENT

Clean all equipment with Turpentine immediately after use.

Paintcor cc
Reg No: CK 86/19456/23
VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za
Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited

