

PAINTCOR

SUPREME QUALITY *Since 1986*

POOLCURE

Technical Specifications

Vehicle Type	Epoxy
Solvent	No Solvent
Enviro Rating	Flammable 3
Dilution / Thinning	This product is supplied ready for use.
Theoretical Spread Rate	8m ² per litre per coat.
Apply with	Brush or Roller
Drying time	@ 25°C – 6 hours overcoat
Wash ability	Excellent
Elongation	N/A
Pigment	Pigmented to standard colours
Solids Volume	98 - 99%
Flexibility	Poor
Colour	Black, Blue, White
Finish	Gloss
Storage	Cool, dry place. Keep out of reach of children.
Over coating	Between Primer & Top coat: 6 hours @25°C Between top coats: 12 hours @25°C
Packaging	1L, 5L
Guarantee	N/A
Conditions of Guarantee	N/A
Resistance to Water	Excellent
Resistance to Solvents	Excellent
Impact Resistance	Excellent
Active Ingredient	N/A
Additional Amount	N/A
Caution	Flammable
Catalyst Ratio	25.5gms Catalyst to 100gms Base
Recommended Dry Film	90um per coat
Freeze Thaw	Pass
Accelerated Stability	Pass
Accelerated Weathering	Good
Appearance	Black, Blue or White

Note: Application directions must be strictly followed for this product to perform to its full potential. This product carries no guarantee once applied.

Paintcor cc
Reg No: CK 86/19456/23
VAT No: 4830119311

Members: G. Williams, G. Adendorff
W. Williams

Head office: 1494 Mailship
street, Laser Park, Honeydew, 2040
Postal Address: P.O. Box 917,
Northriding, 2162
RSA

Email
sale@paintcor.co.za
Website
www.paintcor.co.za

Tel: 011 794 2885
Fax no: 011 794 6955
Emergency Numbers
+27(0) 79 526 1565
+27(0) 84 305 5636



SABS
ISO 9001 Accredited

